

Synthesis of Silver Nanoparticles from Plant and Fruit Extracts- Summary on Research and Studies

Dr. Sunil Jayant Kulkarni

Chemical Engineering Department, Datta Meghe College of Engineering, Airoli, Navi Mumbai, Maharashtra, India

ABSTRACT

Nanoparticles can be synthesized by various methods such as gas condensation, attrition, chemical precipitation, pyrolysis and hydrothermal synthesis. These nanomaterials find application in paint and pigment industry, electrical equipments and chemical processing industries. The enhancement of heat transfer coefficient by nanofluids is also widely discussed and investigated research area. Carbon nanotubes are used in antennas. They also find application in selective removal of some pollutants by adsorption. The high surface to volume ratio makes them highly catalytic and reactive. Synthesis of the nanoparticles can be carried out by various physical, physico-chemical and biological methods. Current review summarizes research and studies on synthesis of silver nanoparticles from plant extracts. Silver nanoparticles are finding importance because of wide range of applications due to unique optical, electrical, and thermal properties. High electrical conductivity, stability, and low sintering temperatures are some important features of nanoparticles.

Keywords: Capping Agents, Reducing Agents, Stability, Extract, Properties.

I. INTRODUCTION

Particles between 1 and 100 nanometers (nm) in size are termed as nanoparticles. It is postulated that the properties of materials change significantly, as their size approaches the nanoscale. As we know, for the particles larger than 1 micron, the percentage of the surface is insignificant in relation to the volume in the bulk of the material. The surface area gains significance when we talk about particles at nano level. Nanoparticles melt at much lower temperature.

Nanoparticles can be synthesized by various methods like attrition, precipitation, pyrolysis, hydrothermal synthesis. These nanomaterials are finding increasing applications in paint and pigment industry, electrical equipments and chemical processing industries [1-4]. The enhancement of heat transfer coefficient by nanofluids is also widely discussed and investigated research area [5-9]. Carbon nanotubes are used in antennas. They also find application in selective removal of some pollutants by adsorption [10,11]. The high surface to volume ratio makes them highly catalytic and reactive. Synthesis of the nanoparticles can be carried

out by various physical, physico-chemical and biological methods. Silver nanoparticles are finding importance because of wide range of applications due to their unique optical, electrical, and thermal properties. High electrical conductivity, stability, and low sintering temperatures are some important features of nanoparticles. Current review summarizes research and studies on synthesis of silver nanoparticles from plant extracts.

II. SYNTHESIS OF SILVER NANOPARTICLES FROM PLANT AND FRUIT EXTRACTS

Mohammadlou et.al. carried out an investigation on synthesis of silver nanoparticles from plants [12]. Their investigation indicated that for synthesis of AgNPs, natural compounds that are present in plant extracts can act as both reducing and stabilizing agents. The natural capping agents such as proteins impart stability to AgNPs. Eco-friendliness, biocompatibility and cost-effectiveness are few advantages of synthesis of AgNP from plant extracts. Agrawal et.al. investigated synthesis of silver nanoparticles [13]. They used *Azadirachta indica* extract for synthesis of nanoparticles. In their

work, they optimized parameters like temperature, size, and stirring conditions. They found that the carbonyl groups from the amino acid residues and proteins were responsible for binding of the metal ions.

Umoren et.al.carried out investigation on green synthesis and characterization of silver nanoparticles [14].They carried out investigation with red apple (*malus domestica*) fruit extract at room temperature. The fruit extract acted as reducing and capping agents. The negative value of zeta potential indicated that the synthesized silver nanoparticles were stable at room temperature. Awed and Salem investigated synthesis of silver nanoparticles from mulberry leaves extract [15].Their analysis indicated that the silver nanoparticles formed by the reduction of Ag^+ ions by the mulberry leaves extract were crystalline in nature. The main advantages of green chemistry are ease with which the process can be scaled up and economic viability. They claimed that their method for synthesis of nanoparticles was a fast, eco-friendly and convenient.Gavhane et.al used extract of neem leaf and triphala for extraction of silver nanoparticles [16]. They also evaluated their antibacterial activities. Their analysis indicated that the silver nanoparticles were predominantly spherical in nature. Their research also indicated that neem and triphala synthesized silver nanoparticles inhibited the growth of gentamycin and ampicillin resistant *k. pneumoniae*.

Abubakar et.al.carried out investigation on black carrot root extract for synthesis of silver nanoparticles [17].They reiterated the advantages of green technology such as cost-effectivity, energy-efficiency and easy methodology. Anjum et.al. carried out investigation on plant-mediated green synthesis of silver nanoparticles[18].They also discussed various aspects of mechanistic aspects involved in reduction and stabilization of AgNPs. ForAgNP synthesis, plant derived methods have advantages such as choices available, and the benefit of faster synthesis over other methods.Yamini et.al.carried out investigation on silver nanoparticle synthesis using cleome viscosa [19]. They explained development of novel technologies. In this work, they described a cost effective and environment friendly technique for green synthesis. They used the extract of *Cleome viscosa* as reducing as well as capping agent.

Panigrahi and Zha carried out an investigation on synthesis and characterization of silver nanoparticles [20]. They used leaf extract of *azadirachta indica*.They observed more than 90% of reduction of Ag^+ ions in 4 Hrs.They found that *Azadirachta indica* had better potential to reduce Ag ions into Ag nanoparticles than *Acorus calamus* extract. Rath et.al.carried out review on development of reliable and eco-friendly process for synthesis of nanoparticles [21]. Silver nanoparticles are widely discussed and investigated due to physical, chemical and biological properties. Prathibha et.al.carried out investigation on used of fruit extracts of *terminalia chebula* retz. for synthesis of nanoparticles [22].They prepared the aqueous and methanolic fruit extracts. Change of the color of the solution from yellowish brown to dark brown confirmed formation of nanoparticles. Compared to methanolic and aqueous extracts, they found that the aqueous extract containing silver nanoparticles was more resistant to all the microorganisms. An investigation was carried out by Christopher et.al. for biosynthesis of silver nanoparticles using leaf extract [23]. They used leaf extract of *Aegle marmelos*.They obtained the maximum silver nanoparticle synthesis at 2:1 ratio.6 mM silver nitrate and pH 6 indicated highest peak.

Hazarika et.al. carried out investigation on phytochemical screening and synthesis of silver nanoparticles [24]. They used leaf extract of *rhynchochloa ellipticum*.To find the presence of various phytochemicals, they investigated the hexane and ethanol extracts of the leaves. They concluded that ethanol extract of the plant was a very good bioreductant for the synthesis of silver nanoparticles. Christensen et.al.carried investigation on biosynthesis of silver nanoparticles using *Murraya koenigii* leaf extract [25]. Also they reported the effect of broth concentration in reduction mechanism and particle size. Their analysis indicated that the nanoparticles were crystalline in nature. They also observed that the rate of reduction increased with increasing broth concentration. There was decrease in particle size with broth concentration. Mittal et.al. reviewed the metallic nanoparticle synthesis by using plants[26]. These nanoparticles are free from the toxic contaminants and hence are suitable for therapeutic applications. Also this type of synthesis provides a controlled size and morphology.Shivashankar and Sisodia used inexpensive and ecofriendly method for silver nanoparticles[27]. They employed reaction of

biomass of aqueous extracts from plants with aqueous solutions of silver nitrate to obtain silver nanoparticles.

Lalitha et.al. investigated synthesis of silver nanoparticles from leaf extract *Azadirachta indica*[28]. They used *Azadirachta indica* as reducing as well as capping agent. This research again emphasized importance of plant derived nanoparticle synthesis. Gebru et.al. used castor oil (*ricinus communis*), khat (*catha edulis*) and sun flower (*helianthus annuus*) leaf extracts as reducing and stabilizing agents for synthesis of silver nanoparticles[29]. The analysis indicated nanoparticles were face centred cubic structures with crystalline nature. These nanoparticles exhibit antimicrobial activity against two pathogenic bacteria: gram-negative *Escherichia coli* and gram-positive *Staphylococcus aureus*. Indhumathi and Rajathi carried out investigation on silver nanoparticles from the leaves of *Murraya koenigii*[30]. Their studies indicated that the silver nanoparticles obtained from plant extracts had highest activity against *Trichoderma* and *Rhizopus*.

An investigation was carried out by David et.al. on biosynthesis of silver nanoparticles using *Momordica charantia* leaf extract[31]. According to them, eco-friendliness and compatibility for pharmaceutical and other biomedical applications are major advantages of this method. According to them, the reduction and stabilization was caused by the phenolic compounds present in *Momordica charantia* leaf extract. These silver nanoparticles exhibit strong antibacterial activity against *Klebsiella pneumoniae* bacteria. Jayapriya and Lalitha carried out an investigation on the synthesis of silver nanoparticles using aqueous *Ocimum basilicum*(L.)[32]. They used UV-Spectroscopy (UV-Vis), Scanning Electron Microscopy (SEM), X-Ray Diffraction Spectroscopy (XRD) and Fourier Transform Infrared Spectroscopy (FTIR) for analysis of synthesized nanoparticles. Their research indicated that sonication method was able to synthesize the nanoparticles rapidly and easily. Praba et.al. carried out investigation on silver nanoparticles synthesis using *Ficus microcarpa* leaf extract[33]. They used aqueous extracts made from the leaves of *Ficus microcarpa* as reducing agents.

Investigations were carried out by Song and Kim for fast and environment friendly synthesis of silver nanoparticles[34]. They used extracts of five leaves namely pine, persimmon, ginkgo, magnolia and platan

us and carried out comparative studies for the extracellular synthesis of metallic silver nanoparticles. For the quantitative formation of silver nanoparticles, they used UV-visible spectroscopy. Among the leaves used, they found that Magnolia leaf broth was the best reducing agent. Similar research on synthesis of nanoparticles was carried out by Ahmad and Sharma[35]. They used Ultraviolet-Visible (UV-vis) Spectrometer, Energy Dispersive X-ray Analysis (EDAX), Selected Area Diffraction Pattern (SAED) and High Resolution Transmission Electron Microscopy (HRTEM) for analysis. The analysis confirmed crystalline structure of nanoparticles.

An investigation was carried out by Prasad and Venkateswarlu on silver nanoparticles synthesis using soybean seeds extract[36]. They carried out an investigation with different concentration of soybean seed extract, same metal ion concentration and different reaction time on. The characterization of nanoparticles was carried out by UV-vis transmission electron microscopy (TEM), X-ray diffraction (XRD) and FTIR analysis. Habibi et.al. have used the aqueous extract of *Prangos ferulaceae* leaves for extraction of silver nanoparticles [37]. According to them, hydroxyl functional group such as flavanoids, proteins and coumarins are responsible for the reduction and stabilization of silver nanoparticles. They also observed that silver nanoparticles were stable at room temperature. Many investigations are reported on green synthesis of silver nanoparticles [38-43]. These investigations have reported investigation on silver nanoparticles by using plant extracts. Also many of them involved characterization studies[44-47]. Many investigators have studied application of nanoparticles along with synthesis[48-50]. Most of these studies indicated that green synthesis has advantages such as cost, environmental friendliness and ease of operation. It is also fast and energy efficient. The silver nanoparticles were shown to be antibacterial, antifungal and resistant to few infectants and micro organisms.

III. CONCLUSION

Nanomaterials are used in paint and pigment industry, electrical equipments and chemical processing industries. The enhancement of heat transfer coefficient by nanofluids is also widely discussed and investigated research area. Carbon nanotubes are used in

antennas. They also find application in selective removal of some pollutants by adsorption. Most of the studies indicated that green synthesis indicated advantages such as cost, environmental friendliness and ease of operation. It is also fast and energy efficient. The silver nanoparticles were shown to be antibacterial, antifungal and resistant to few infectants and micro organisms. Studies indicate that eco-friendliness and compatibility for pharmaceutical and other biomedical applications are major advantages of this method.

IV. REFERENCES

- [1] Jianli Zou, Lee J. Hubble, K. Swaminathan Iyer And Colin L. Raston(2010). Bare Palladium Nano-Rosettes For Real Time High Performance And Facile Hydrogen Sensing. *Sensors and Actuators B: Chemical*, 150(1), 291–295.
- [2] Anne Aimable, Nathalie Jongen, Andrea Testino, Marcel Donnet, Jacques Lemaître, Heinrich Hofmann, Paul Bowen(2011). Precipitation Of Nanosized And Nanostructured Powders: Process Intensification And Scale-Out Using A Segmented Flow Tubular Reactor (Sftr). *Chem. Eng. Technol.*, 34(3), 344–352.
- [3] Sunil Jayant Kulkarni(2017). Environment friendly synthesis of colour, pigment and dyes: a review. *International Journal of Research and Review*, 4(4), 19-23.
- [4] Wei Yu And Huaqing Xie(2012). A Review On Nanofluids: Preparation, Stability Mechanisms, And Applications. *Journal Of Nanomaterials*, Volume 2012, 17 Pages.
- [5] Puneet Rana and R. Bhargava(2011). Flow and Heat Transfer Analysis of a Nanofluid Along a Vertical Flat Plate with Non-Uniform Heating Using Fem: Effect of Nanoparticle Diameter. *International Journal of Applied Physics and Mathematics*, 1(3), 171-176.
- [6] Sunil Jayant Kulkarni(2014). Process Intensification and Nano-materials: A Short Review. *International Journal of Research*, 1(9), 392-396.
- [7] Dr. Zena K. Kadhim, Dr. Muna S. Kassim, Adel Y. Abdul Hassan(2016). Effect of (MGO) Nanofluid on Heat Transfer Characteristics for Integral Finned Tube Heat Exchanger. *International Journal of Mechanical Engineering and Technology*, 7(2), 11-24.
- [8] Sunil Jayant Kulkarni(2014). Process Intensification and Nano-materials: A Short Review. *International Journal of Research*, 1(9), 392-396.
- [9] Vajravelu Kuppalapalle, Prasad Kerehalli Vinayaka, NG Chiu-On (2013). The Effect of Variable Viscosity on the Flow and Heat Transfer of a Viscous Ag- water and Cu-water Nanofluids. *Journal of Hydrodynamics*, 25(1), 1-9.
- [10] Boparai H.K., Meera J., Carroll D.O.(2010). Kinetics and thermodynamics of cadmium ion removal by adsorption onto nano zerovalent iron particles. *J Hazardous Mater*, 15, 1-8.
- [11] Sunil J. Kulkarni, Dr. Jayant P. Kaware (2013). Adsorption for Cadmium Removal from Effluent- A Review. *International Journal of Science, Engineering and Technology Research*, 2(10), 1840-1844.
- [12] Mohammadlou, M., Maghsoudi, H. and Jafarizadeh-Malmiri, H.(2016). A review on green silver nanoparticles based on plants: Synthesis, potential applications and eco-friendly approach. *International Food Research Journal*, 23(2), 446-463.
- [13] Pushpa Agrawal, Karan Mehta, Pooja Vashisth, Sudarshan, Preethi Bhat, B V Goutham Vishnu(2014). Green Synthesis Of Silver Nanoparticles And their Application In Dental Filling Material. *International Journal of Innovative Research in Science, Engineering and Technology*, 3(6), 1338-1352.
- [14] S. A. Umoren, I. B. Obot, Z. M. Gasem(2014). Green Synthesis and Characterization of Silver Nanoparticles Using Red Apple (*Malus domestica*) Fruit Extract at Room Temperature. *J. Mater. Environ. Sci.*, 5 (3), 907-914.
- [15] Akl M. Awwad, Nida M. Salem(2012). Green Synthesis of Silver Nanoparticles by Mulberry Leaves Extract. *Nanoscience and Nanotechnology*, 2(4), 125-128.
- [16] Asmita J. Gavhane, P. Padmanabhan, Suresh P. Kamble and Suresh N. Jangle(2012). Synthesis Of Silver Nanoparticles Using Extract Of Neem Leaf And Triphala And Evaluation Of Their Antimicrobial Activities. *Int J Pharm Bio Sci.*, 3(3), 88 – 100.
- [17] Aminu Shehu Abubakar, Ibrahim Bala Salisu, Shiwani Chahal,

- Geetika Sahni, Ramesh Namdeo Pudake (2014). Biosynthesis And Characterization Of Silver Nano Particles Using Black Carrot Root Extract. *Int J Cur Res Rev.*, 6(17), 5-8.
- [18] Sumaira Anjum, Bilal Haider Abbasi and Zabta Khan Shinwari (2016). Plant-Mediated Green Synthesis Of Silver Nanoparticles For Biomedical Applications: Challenges And Opportunities. *Pak. J. Bot.*, 48(4), 1731-1760.
- [19] Yamini Sudha Lakshmi. G. (2011). Green Synthesis of Silver Nanoparticles from *Cleome Viscosa*: Synthesis and Antimicrobial Activity. 2011 International Conference on Bioscience, Biochemistry and Bioinformatics IPCBEE vol.5 (2011) © (2011) IACSIT Press, Singapore, 334-337.
- [20] Tamasa Panigrahi, Dr. Suman Jha (2013). Synthesis And Characterization Of Silver Nanoparticles Using Leaf Extract Of *Azadirachta Indica*. A Thesis Submitted In Partial Fulfillment Of The Requirements For The Degree Of Master Of Science In Life Science, Department Of Life Science National Institute Of Technology Rourkela-769008, Orissa, India, 1-70.
- [21] Monalisha Rath, Swati S Panda and Nabin K Dhal (2014). Synthesis Of Silver Nano Particles From Plant Extract And Its Application In Cancer Treatment: A Review. *International Journal of Plant, Animal and Environmental Sciences*, 4(3), 137-145.
- [22] Prathibha S., Jenitta Emima Packiyam E., Rama Bhat P., Jayadev K. and Shrinidhi Shetty (2015). Green synthesis of silver nanoparticles from fruit extracts of *Terminalia chebula* Retz. and their antibacterial activity. *International Journal of Research in Biosciences*, 4(2), 29-35.
- [23] John Samuel Godwin Christopher, Banerjee Saswati and Panneer Selvam Ezilrani (2015). Optimization of Parameters for Biosynthesis of Silver Nanoparticles Using Leaf Extract of *Aegle marmelos*. *Braz. Arch. Biol. Technol.*, 58(5), 702-710.
- [24] Deepshikha Hazarika, Alakesh Phukan, Eramoni Saikia and Bolin Chetia (2014). Phytochemical Screening And Synthesis Of Silver Nanoparticles Using Leaf Extract Of *Rhynchosyris Ellipticum*. *International Journal of Pharmacy and Pharmaceutical Sciences*, 6(1), 672-674.
- [25] Laura Christensen, Singaravelu Vivekanandhan, Manjusri Misra, Amar Kumar Mohanty (2011). Phytochemical Screening and Synthesis of Silver Nanoparticles Using Leaf Extract Of *Rhynchosyris Ellipticum*. *Adv. Mat. Lett.*, 2(6), 429-434.
- [26] Amit Kumar Mittal, Yusuf Chisti, Uttam Chand Banerjee (2013). Synthesis of metallic nanoparticles using plant extracts. *Biotechnology Advances*, 346-356.
- [27] M Shivashankar and Garvit Sisodia (2012). Biosynthesis Of Silver Nanoparticles Obtained From Plant Extracts Of *Moringa Oleifera*. *Int. J. Life Sc. B and Pharm. Res.*, 1(3), 182-185.
- [28] A. Lalitha, R. Subbaiya and P. Ponmurugan (2013). Green synthesis of silver nanoparticles from leaf extract *Azadirachta indica* and to study its antibacterial and antioxidant property. *Int. J. Curr. Microbiol. App. Sci.*, 2(6), 228-235.
- [29] Hailemariam Gebru, Abi Tadesse, Jyotsna Kaushal and O. P. Yadav (2013). Green Synthesis of Silver Nanoparticles and their Antibacterial Activity. *J. Surface Sci. Technol.*, 29(1-2), 47-66.
- [30] Indhumathi. T. K. Rajathi (2013). A study on synthesis of silver Nanoparticles from *Murrayakoengii* leaf and its Antifungal activity. *Int. J. Drug Dev. and Res.*, 5(3), 293-298.
- [31] Samuel Alwin David, Kanagasabai Muruganandam Ponvel, Mohamed Anis Fathima, Solaiappan Anita, Jeyapaul Ashli and Alaguvel Athilakshmi (2014). Biosynthesis of silver nanoparticles by *Momordica charantia* leaf extract: Characterization and their antimicrobial activities. *J. Nat. Prod. Plant Resour.*, 4 (6), 1-8.
- [32] E. Jayapriya and P. Lalitha (2013). Synthesis of Silver Nanoparticles using Leaf Aqueous Extract of *Ocimum basilicum* (L.). *International Journal of ChemTech Research*, 5(6), 2985-2992.
- [33] P. Shanmuga Praba, V. S. Vasantha, J. Jeyasundari and Y. Brightson, Arul Jacob (2015). Synthesis Of Plant-Mediated Silver Nanoparticles Using *Ficus Microcarpa* Leaf Extract And Evaluation Of Their Antibacterial Activities. *Eur. Chem. Bull.*, 4(3), 116-120.
- [34] Jae Yong Song, Beom Soo Kim (2009). Rapid biological synthesis of silver nanoparticles using plant leaf extracts. *Bioprocess Biosyst Eng*, 32, 79-84.

- [35] Naheed Ahmad, Seema Sharma (2012). Green Synthesis of Silver Nanoparticles Using Extracts of *Ananas comosus*. *Green and Sustainable Chemistry*, 2, 141-147.
- [36] Ch. Prasad, Ponneri Venkateswarlu (2014). Soybean Seeds Extract Based Green Synthesis of Silver Nanoparticles. *Indian Journal of Advances in Chemical Science*, 2(3), 208-211.
- [37] Biuck Habibi, Houriyeh Hadilou, Saeed Mollaei, Alireza Yazdinezhad (2017). Green synthesis of Silver nanoparticles using the aqueous extract of *Prangos ferulacea* leaves. *Int. J. Nano Dimens.*, 8 (2), 132-141.
- [38] Sohail Yasin, Lin Liu, Juming Yao (2013). Biosynthesis of Silver Nanoparticles by Bamboo Leaves Extract and Their Antimicrobial Activity. *Journal of Fiber Bioengineering and Informatics*, 6(1), 77-84.
- [39] Deepika Gupta, Pramila Chavan (2017). Green Synthesis of Silver Nanoparticles Involving Extract of Plants of Different Taxonomic Groups. *J. Nanomed Res.*, 5(2), 001-10
- [40] Pooja Moteriya, Hemali Padalia and Sumitra Chanda (2014). Green biosynthesis of silver nanoparticles using *Psidium guajava* L. leaf extract and antibacterial activity against some pathogenic microorganisms. *Journal of Pharmacy Research*, 8(11), 1579-1585.
- [41] Jeyanthi Palanivelu, Merin Mary Kunjumon, Anushree Suresh, Ashwini Nair, Dr. Ramalingam C. (2015). Green Synthesis of Silver Nanoparticles from *Dracaena mahatma* Leaf Extract and its Antimicrobial Activity. *J. Pharm. Sci. and Res.*, 7(9), 690-695.
- [42] Raksha Pandit (2015). Green Synthesis Of Silver Nanoparticles From Seed Extract Of *Brassica Nigra* And Its Antibacterial Activity. *Nusantara Bioscience*, 7(1), 15-19.
- [43] Reza Teimuri-Mofrad, Raha Hadi, Behnam Tahmasebi, Sana Farhoudian, Maryam Mehravar, Ramin Nasiri (2017). Green Synthesis Of Gold Nanoparticles Using Plant Extract: Mini-Review. *Nanochem Res*, 2(1), 1-7.
- [44] M. Jannathul Firdhouse, P. Lalitha and Shubashini K. Sripathi (2012). Novel Synthesis Of Silver Nanoparticles Using Leaf Ethanol Extract Of *Pisonia Grandis* (R. Br). *Der PharmaChemica*, 4(6), 2320-2326.
- [45] R. Uma Maheswari, A. Lakshmi Prabha, V. Nandagopalan and V. Anburaja (2012). Green Synthesis Of Silver Nanoparticles By Using Rhizome Extract Of *Dioscorea oppositifolia* L. And Their Anti Microbial Activity Against Human Pathogens. *IOSR Journal Of Pharmacy And Biological Sciences (IOSRJPBS)*, 1(2), 38-42.
- [46] Ahmed A. Moosa, Ali Mousa Ridha and Mustafa Al-Kaser (2015). Process Parameters For Green Synthesis Of Silver Nanoparticles Using Leaves Extract Of Aloe Vera Plant. *Int. J. Of Multidisciplinary And Current Research*, 3, 966-975.
- [47] Masoud Negahdary, Shahin Omidi, Ali Eghbali-Zarch, Seyed Abdolhossein Mousavi, Gholamreza Mohseni, Yazdan Moradpour Ghasem Rahimi (2015). Plant Synthesis Of Silver Nanoparticles Using *Matricaria Chamomilla* Plant And Evaluation Of Its Antibacterial And Antifungal Effects. *Biomedical Research*, 26 (4), 794-799.
- [48] J.M. Sila, I. Kiiro, F.B. Mwaura, I. Michira, D. Abongo, E. Iwuoha and G.N. Kamau (2014). Green Synthesis Of Silver Nanoparticles Using *Eucalyptus Corymbia* Leaves Extract And Antimicrobial Applications. *International Journal Of Biochemiphysics*, 22, 21-30.
- [49] Mahipal S. Shekhawat, M. Manokari, N. Kannan, J. Revathi, R. Latha (2013). Synthesis Of Silver Nanoparticles Using *Cardiospermum Halicacabum* L. Leaf Extract And Their Characterization. *The Journal Of Phytopharmacology*, 2(5), 15-20.
- [50] G. Durga Devi, K. Muruganand C. Panneer Selvam (2014). Green Synthesis Of Silver Nanoparticles Using *Euphorbia Hirta* (Euphorbiaceae) Leaf Extract Against Crop Pest Of Cotton Bollworm *Helicoverpa Armigera* (Lepidoptera: Noctuidae). *J. biopest*, 7(Supp.), 54-66.